

BOSSAUTO INNOVA, S.A. Pol. Ind. Validoriolf O' Thomas Edison 16, 08430 La Roca del Vallés. Barcelona

t: +34 938 604 923 / f: +34 938 712 336 info@bossauto.com / www.bossauto.com



# TECHNICAL DATA SHEET

## 1. IDENTIFICATION OF THE PRODUCT AND THE COMPANY

NAME OF THE PRODUCT	Double-sided adhesive tape		
CODE	040010 (6 mmx10 m) 040011 (9 mmx 10 m) 040012 (12 mmx10 m) 040013 (19 mmx10 m) 040014 (25 mmx 10 m)		
DISTRIBUTOR	BOSSAUTO INNOVA, S.A.		
ADDRESS	c/ Thomas Edison 16, Apartado de correos 95		
CITY	08430 La Roca del Vallés (Barcelona) SPAIN		
PHONE	+ 34 93 860 49 23		
FAX	+34 93 871 23 36		
E-MAIL	info@bossauto.com		
WEB	www.bossauto.com		

## 2. DESCRIPTION

Double sided adhesive tape is especially designed for permanent bonding in interior and exterior applications. This can replace reveting, welding, liquid glues and other permanents fasteners. It is also suitable for various kinds of substances, such as metal, wool, glass and many plastics.

## 3. ADHESIVE

- Permanent crossed linked solvent acrylic adhesive.
- Pressure sensitive, providing high tack.
- Excellent shear performance.

#### 4. CARRIER

- 1.0 mm black closed cell cross linked Polyethylene foam
- Density: 100kg/m³

## 5. LINER

- High quality paper LDPE liner red
- Easy to release

## 6. TEHCNICAL DETAILS

180º peel adhesion on stainless steel	1100g/10mm
Tensile strength	4kg/cm <sup>2</sup>
Elongation	200%



## BOSSAUTO INNOVA, S.A.

Pol. Ind. Valldoriolf C<sup>2</sup> Thomas Edison 16, 08430 La Roca del Vallés. Barcelona t: +34 938 604 923 / f: +34 938 712 336 info@bossauto.com/www.bossauto.com



Service temperature range	-20°C>+120°C
Solvent resistance	Good
UV-resistance	Good
Moisture resistance	Good

## 7. APPLICATION

- Fixing exterior trims and parts
- Panel mounting
- Signs and panels
- Interior and exterior use
- Temperature: between +15°C and +30°C. Surface must be clean and free from dust and grease. Pressure sensitive adhesive must be applied with a maximum of pressure in order to achieve maximum pressure level. The indicated level of performance will be reached after a bonding period of 24 hours at 23°C.

## 8. STORAGE AND SHELF LIFE

Clean and dry in a well ventilated area, preferably at a temperature between 10°C and 30°C. Stored under these conditions shelf life will be a minimum of one year.

The technical information is given in good faith, but the user should assure himself that the performance of the product is sufficient for this application. The quoted values are average and should not be taken as maximum or minimum values for specific purposes. Boss Auto Import cannot be held responsible for product failure unless full testing has been carried out. The client has to decide on the tapes suitability for own applications.