

## Technical Information 1K Spray Putty



ColorMatic 1K spray putty offers extremely high filling power and durability. It is ideal for levelling large uneven areas on sanded undercoats and provides very good adhesion to polyester filler, plastics and metals.

### Application:

Ideal for spot repairs and refinishing parts

## Quality and properties

- Very high filling power and durability
- Very good adhesion to polyester filler, plastic and metal
- Simple, time-saving application
- Fast drying time
- Good flow
- Not recoatable with: 1K Füllprimer HG1 und HG7

## Physical and chemical data

- **Basis of binder:** Acrylic resin
- **Colour:** beige
- **Smell:** solvent
- **Efficiency:**  
400ml are sufficient for approx. 1,25 - 1,75 m<sup>2</sup>
- **Substrate:**  
blank sheet steel, sanded, priming of spare parts, sanded, cured paintings, sanded, polyester substrates, sanded
- **Temperature resistance:** to 110°C
- **Storage stability:**  
24 month if appropriate storage provided
- **Size:**  
Aerosol cans, maximum nominal volume 400 ml
- **VOC-value:** 240,1g

## Environment and labelling

**Environmentally compatible:** MOTIP DUPLI is committed to apply formulations without restricted or critical ingredients and to achieve best possible performance. The caps and packagings are made of recyclable material.


**Disposal:** Please mind the residue inside the containers. Completely emptied containers can be used for recycling. If cans are not emptied, they should be disposed off as "special refuse".

**Labelling:** All products of MOTIP DUPLI comply with the current status of their labelling regulations. Classification and distinction takes place by the presently legal form of the **Globally Harmonized System of Classification and Labelling of Chemicals** (GHS) or rather by CLP 1272/2008/EG regulations. Our safety data sheets comply with the current form of REACH 1907/2006/EG, article 31 und appendix II,

## Using instructions

**Before use, carefully read and observe the warning texts on the label!**

- Remove all rust from damaged area and sand
- Damaged area must be dry and free of dust and grease
- Shake the can well for 2 minutes
- Carry out spray test
- Attention: after sanding thoroughly clean surface with water-based cleaner. Don't use solvent-based cleaner.
- **For professional use only**
- **Wear an adequate respirator (we recommended type A2/P3)**



## Disclaimer of liability

This application-technological information is given to the best of our knowledge. The notes mentioned herein are, however, non-binding and do not exempt you from own tests to see whether the products supplied by us are suitable for your special application. The use and processing is beyond our control and therefore exclusively in the responsibility of the user. MOTIP DUPLI is let off the liability, unless the liability-based incident is caused by a fault incurred to MOTIP DUPLI.

malfunction is caused by a fault in the control system.

For any further technical questions call our hotline +49 (0) 62 66 75-266 from Monday to Thursday from 9 h a.m. to 3 h p.m. or on Friday until 12 h p.m.

As of July 26, 2010

This release replaces all eventually earlier issued versions.

Print date: 17.06.2019

MOTIP DUPLI GmbH | Kurt-Vogelsang-Straße 6 | 74855 Haßmersheim | [info@de.motipdupli.com](mailto:info@de.motipdupli.com)